



Dear Customer,

20.04.2015

The products which have been produced by coil coating technology need to have a special cleaning and maintenance program. In most cases, annual or suggested frequency according to enviromental conditions would be required to keep the lacquered coated surface long-term quality.

The Required Cleaning Rules Are At The below :

- Firstly wash the surface with clean water
- Clean the surface with water and mild detergent, followed by a clean water rinse. Use sponge, leather or wiper is necessary to avoid water stains.
- Cleaning agents must have pH between 5-8 values.
- If the soil is still adhering after dry, then 5-10% IPA (Isopropyl Alcohol) solution will be necessary.
- it should be used with soft sponges and/or soft rags. The washing should be done with uniform pressure.
- After washing, the surface should be thoroughly rinsed with clean water, and the rinsed surface is air-dried or wiped with squeegee or lint-free cloth

NOTE:

Do not do these;

- Do not clean sun-heated surfaces (above 40 °C) to avoid rapid drying which may lead to stain formation
- Do not use strong alkali (such as potassium hydroxide, sodium hydroxide/caustic soda) and strong acid and/or abrasive cleaners. If these solvents and cleaners were used, the paint might be swelled or removed.
- Do not use strong organic solvents, such as MEK (Methyl Ethyl Ketone), MIBK (Methyl Iso-butyl Ketone), Triclene and paint thinner.
- Do not mix different cleaners. If cleaners needed to be mixed, please follow the manufacturer's instructions.
- Do not use abrasive pads such as wools or sandpapers for cleaning.
- Do not use sea water for cleaning.

Best Regards,

Egemen YÖRÜR

Quality Manager

SİSTEM METAL YAPI
REKLAM MALZ. VE İNŞ. SAN. TİC. A.Ş.
İstiklal Mh. Atatürk Cd. 19 Mayıs İş Mrk. No.:1
Kıraç-Esenyurt/İST. Tic. Sic. No.: 471585
Marmara Kurumlar V.D.: 771 018 0969

İsmail HAŞİMOĞLU

Technical Director

Address: Merkez Mah. Ali Osman Çelebi Bulv. No:140 59860 Çorlu, Tekirdağ, Türkiye
Tel: +90 282 661 10 10
Fax: +90 282 661 10 11

KEMAH
GROUP